



PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau


## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 7 : <b>D21F 1/44, D21H 21/42</b>		(11) International Publication Number: <b>WO 00/39391</b>	
A1		(43) International Publication Date: 6 July 2000 (06.07.00)	
(21) International Application Number: PCT/GB99/04257		(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).	
(22) International Filing Date: 16 December 1999 (16.12.99)		Published With international search report.	
(30) Priority Data: 9828770.9 29 December 1998 (29.12.98) GB			
(71) Applicant (for all designated States except US): DE LA RUE INTERNATIONAL LIMITED [GB/GB]; De La Rue House, Jays Close, Basingstoke, Hampshire RG22 4BS (GB).			
(72) Inventors; and (75) Inventors/Applicants (for US only): ISHERWOOD, Roland [GB/GB]; 1 Paul's Heath Cottage, Cole Henley, Whitechurch, Hampshire RG28 7QJ (GB). RIDYARD, Stephen, David [GB/GB]; 7 Seaford Road, Bradshaw, Bolton BL2 4BY (GB).			
(74) Agent: BOULT WADE TENNANT; Verulam Gardens, 70 Gray's Inn Road, London WC1X 8BT (GB).			

(54) Title: IMPROVEMENTS IN MAKING PAPER

## (57) Abstract

This invention is directed to improvements in paper incorporating an elongate impermeable element, to a method of making such paper and to documents made therefrom. The invention therefore comprises a method of making single ply paper having an elongate impermeable strip at least partially embedded therein, comprising the steps of blinding one or more selected areas of a porous support surface, depositing a first layer of paper fibres onto the porous support surface around the blinded areas, bringing the strip to lie in contact with the blinded areas of the support surface such that at least edges of the strip over lie the deposited fibres, and depositing a further layer of paper fibres over the first layer and the impermeable strip to securely embed the edges of the strip within the paper, said blinded areas being impermeable to substantially prevent the deposition of fibres thereon before the security element is laid thereover and to thereby form a plurality of discrete translucent or transparent windows in a first surface of the paper in which regions of one side of the strip are exposed, wherein substantially no paper fibres are deposited along on an opposite side of the length of the strip in a region between the edges to thereby expose a continuous area of the strip at a second surface of the paper.



IMPROVEMENTS IN MAKING PAPER

This invention is directed to improvements in paper incorporating an elongate impermeable element, to a method of making such paper and to documents made therefrom.

It is generally known to include in security paper, as a security feature, elongate security elements such as threads, strips or ribbons of, for example, plastics film, metal foil, metallised plastic, metal wire. These security elements are included in the thickness of security paper to render imitation of documents produced from the paper more difficult. These elements help in the verification of security documents as they render the view of the documents in reflected light different from that in transmitted light. To increase the security provided by the inclusion of such an elongate element, it is also known to endow the element itself with one or more verifiable properties over and above its presence or absence. Such additional properties include magnetic properties, electrical conductivities, the ability to absorb x-rays and fluorescents.

As a further security feature, it has been found to be particularly advantageous to provide windows in one side of the surface of the paper, which expose such elongate elements at spaced locations. Examples of methods of manufacturing such paper incorporating security elements with or without windows as described below. It should be noted that references to "windowed thread paper" include windowed paper incorporating any elongate security element.

EP-A-0059056 describes a method of manufacture of windowed thread paper on a cylinder mould paper-making machine. The technique involves embossing the cylinder mould cover and bringing an impermeable elongate security element into contact with the raised

- 2 -

regions of an embossed mould cover, prior to the contact entry point into a vat of aqueous stock. Where the impermeable security element makes intimate contact with the raised regions of the embossing, no fibre deposition can occur. After the paper is fully formed and couched from the cylinder mould cover, the contact points are present as exposed regions which ultimately form windows, visible in reflected light, on one side of a banknote paper.

WO-A-93/08327 describes a method of manufacturing windowed thread paper on a Fourdrinier paper-making machine. A rotating embedment means, with a modified profile for embossing, is used to drive an impermeable elongate security element into draining paper stock, on a Fourdrinier wire. The profile of the embedment means is such that raised portions are provided which remain in contact with the security element during the embedment process. Thus, paper fibres are prevented from collecting between the security element and embedment means, such that the security element is subsequently exposed in windowed regions of paper.

For production reasons, the security element used in windowed or non-windowed paper is oscillated within the paper substrate by a small amount, for example, plus or minus 6mm from either side of a centre line. This is primarily to assist cutting and guillotining across the thread tracks of stacks of 500 sheets. If the thread was not oscillated, the guillotine blade would be presented with a very sharply defined area, of say 1 to 2mm wide, of polymer/metal/paper built up from 500 sheets. This tends to blunt or even chip the cutting blade. By oscillating the thread, this area is distributed over a wider area of 10 to 15mm, easing the passage of the blade through the 500 sheet stack. The result of thread oscillation is that only parallel bars can be used in the design of the windows, if the banknotes made from the paper are all to look the

- 3 -

same.

Recent investigations have shown that impermeable threads of 4mm to 6mm maximum width can be included in paper using the above methods of paper-making. This is due to the requirement for paper stock to flow around the thread and form complete paper areas on the front of the thread in the finished document.

In Canadian patent specification CA-A-2,122,528, there is described an anti-falsification paper which incorporates a wide impermeable security strip with a width between 2mm and 4mm. The paper is of multiply design, with at least two paper layers produced on separate paper machines. The security strip is embedded in a first ply and has perforations along the edges which permit water drainage and hence paper fibre deposition along the edges of the thread. The front of the strip is laid down over raised areas on the embossed cylinder mould cover before the raised areas enter the vat of paper stock so as to create windows of exposed strip in the contact regions. The width of the raised areas is narrower than the strip width to permit permeation through the perforations of the strip by paper fibres. However, the width of strip is so great that the paper formed on the back of the paper has flaws in the form of arbitrary holes in the region of the strip. A second ply of ordinary paper is independently formed and the two are laminated together and further processed, the second ply thereby covering the flaws in the back of the first ply and providing at least one homogenous paper surface. In another embodiment, a third ply is laminated over the front of the first ply to wholly embed the security strip. In yet another embodiment, the width of the strip is selected to be so wide that no paper forms on the back of the first paper ply to provide a continuous exposed area on the back. The front of the strip is laid on a continuous raised area

- 4 -

on the mould cover before the raised areas enter the vat of paper stock to provide a continuous exposed area on the front. A second ply of paper is then laminated to the first ply to form the finished security paper and give a homogenous paper layer on one side and a continuous exposed strip on the other.

In all of the prior art methods described above, the width of the elongate element which can be used is very limited. Furthermore, the areas of the threads which are exposed are restricted in terms of shape, due to the limitation imposed by the required embossings, and in terms of the areas, due to the nature of the paper-making technique itself.

One object of the present invention is therefore improved method of manufacturing to provide a paper containing a wide impermeable substrate which can be used as a security or non-security feature to describe windows or decorative patterns.

According to the invention there is therefore provided a method of making single ply paper having an elongate impermeable strip at least partially embedded therein, comprising the steps of blinding one or more selected areas of a porous support surface, depositing a first layer of paper fibres onto the porous support surface around the blinded areas, bringing the strip to lie in contact with the blinded areas of the support surface such that at least edges of the strip over lie the deposited fibres, and depositing a further layer of paper fibres over the first layer and the impermeable strip to securely embed the edges of the strip within the paper, said blinded areas being impermeable to substantially prevent the deposition of fibres thereon before the security element is laid thereover and to thereby form a plurality of discrete translucent or transparent windows in a first surface of the paper in which regions of one side of the strip are exposed,

- 5 -

wherein substantially no paper fibres are deposited along an opposite side of the length of the strip in a region between the edges to thereby expose a continuous area of the strip at a second surface of the paper.

The preferred prior art production methods for windowed security paper require an embossed cylinder mould cover. The use of blinding is not generally used in paper-making techniques for the very reason that the paper is preferred to be uniform and consistent. The appearance of holes and perforations is not a feature which is usually required. One exception is the paper used for making tea bags, but the method of manufacturing such paper does not include blinds.

As the impermeable strip contacts the support surface after some paper fibres have already been deposited round the blinded areas, it prevents any further fibre deposition over the blinded areas preserving the designs created in the blinding operation as clear areas. Whilst the use of embossed cylinder moulds covers restricts the width of security threads which can be embedded, with the method of the present invention it is possible to produce a document with any width of impermeable strip, up to full document width, with paper "coatings" in any design, including watermarks, on the front side of the document. The back of the paper can be made to contain a continuous exposed strip which can be used for the display of indicia and the like.

An adhesive is preferably applied to tie one side of the strip before bringing that side into contact with the support surface.

An adhesive is preferably applied to one or more portions of the other side of the strip.

The strip is preferably not oscillated during manufacture of the paper.

- 6 -

This provides an advantage in design terms as it means that more precised and detailed patterns can be created around the strip.

5 The invention further provides single ply paper made by the above mentioned method having first and second surfaces and an elongate impermeable strip, in which the edges of the strip are embedded fully between the first and second surfaces, and a continuous strip of a central section of the strip is  
10 exposed at the first surface of the paper and at least partially covered by a layer of paper of reduced opacity forming the second surface.

The second surface of the paper is preferably provided with a plurality of discrete windows in which  
15 portions of the strip are exposed at intervals.

The width of the strip preferably lies in the range of 6 to 25mm.

Such a broad width advantageously ensures that few or no fibres are deposited thereon. The width of  
20 the strip more preferably lies in the range of 8 to 10mm.

Preferably the strip bears indicia, images or information.

Preferably the strip is wholly or partially  
25 metallised or bears one or more holographic images.

The strip has preferably one or more colour shift areas and/or has at least one security embossing.

The strip may be printed on one or both sides and/or may bear a liquid crystal material.

30 The strip preferably has a thickness of 25 to 100 micrometers and more preferably of 50 micrometers.

One side of the strip is preferably coated with an adhesive.

35 The other side of the strip may be partially coated with an adhesive in regions such that some paper is formed in the adhesive regions to provide paper patterns along the exposed central section of

- 7 -

the strip.

The invention also provides a document produced from the aforementioned paper or a security document.

5       The invention will now be described, by way of example only, with reference to the accompanying drawings in which:

10       Figure 1 is a cross-sectional side elevation of a schematic of a paper-making vat for use in the method and manufacturing of paper according to the present invention;

15       Figures 2 to 6 are cross-sectional side elevations of the steps involved in the method of forming paper according to the present invention;

20       Figure 7 is a plan view of the section of the cylinder mould cover for use in making an alternative embodiment of paper according to the present invention by blinding only;

25       Figure 8 is a cross-sectional side elevation of the cylinder mould cover of figure 7 on the line VIII-VIII;

30       Figure 9 is a cross sectional side elevation paper formed on the cylinder mould cover of Figure 7, taken on the line IX-IX Figure 10;

Figure 10 is a plan view of the paper Figure 9;

35       Figure 11 is a cross-sectional side elevation of the paper of Figure 10 taken on the line XI-XI;

Figures 12 to 16 are similar views to those of Figures 7 to 11 showing a more complex design formed



- 8 -

by blinding;

Figure 17 is a plan view of a section of a cylinder mould cover for use in making one embodiment of paper according to the present invention by embossing and blinding;

Figure 18 is a cross-sectional side elevation of the cylinder mould cover of Figure 7 on the line XVIII-XVIII;

Figure 19 is the same cross-sectional elevation as Figure 8 showing partial deposition of paper fibres during a paper-making process;

Figure 20 is the same cross-sectional elevation as Figures 18 and 19 showing an impermeable element laid over the cylinder mould cover;

Figure 21 is the same cross-sectional elevation as Figures 18 and 20 showing the paper formed on the cylinder mould cover of Figure 17;

Figure 22 is a plan view of paper formed using the cylinder mould cover of Figure 17 by the steps shown in Figures 18 to 21;

Figures 23 to 26 and 28 and 29 are plan views of alternative papers made according to the invention using different cylinder mould cover layouts; and

Figure 27 is a side cross-sectional elevation of the paper of Figure 26 on the line XXVI-XXVI.

The method of manufacturing paper according to the present invention is illustrated firstly with reference to Figures 1 to 11. A porous support

- 9 -

surface, for example in the form a cylinder mould cover 10, is produced in a known way. The mould cover 10 has no raised areas formed by embossing, such as those described in EP-A-0070172, but selected areas 12 regions are blinded by fixing blinding material to the mould cover 10. The blinding material is typically a metal which is welded to the cylinder mould cover 10 (see Figures 2, 7 and 8), and these blinds define the shape of windows 17 formed in the final paper 16. The blind material 12 may also be wax, polymer or any other material which can be securely attached to the cylinder mould cover 10 to prevent drainage and hence fibre deposition. In this specification the term "window" includes a transparent or translucent region in the paper of regular or irregular shape and occurrence.

In a known manner, the cylinder mould cover 10 is rotated in a vat of paper stock 11 as illustrated in Figure 1. As it rotates, a wide elongate impermeable substrate 13, preferably having a width of 6mm or greater, is brought into contact with the cylinder mould cover 10 below the level of the paper stock 11. This means that a layer 14 of paper fibres has already been deposited onto the cylinder mould cover 10 to form, say, a 40gsm sheet (see Figures 3 and 4). Once the impermeable substrate 13 is brought into contact with the blind material, further paper fibres 15 are deposited on top of and around the sides of the impermeable substrate 13 to form the remainder of the sheet 15 to, typically, 80 to 90gsm (see Figures 5 and 6 or 9). Preferably no oscillation of the impermeable substrate 13 is allowed to take place during manufacture.

Thus, as mentioned above, a layer of paper fibres is laid down on the cylinder mould cover 10 prior to the introduction of the substrate 13. However, whilst the blinded areas 12 would retain little or no

- 10 -

covering of paper fibres before the substrate 13 is  
brought into contact therewith, full coverage is  
obtained in the surrounding areas between the blinded  
areas 12. Equally, because of the impermeable nature  
5 of the substrate 13, there is little or no covering of  
paper fibres retained over the majority of the top of  
the substrate 13. Thus, when the paper 16 is removed  
from the cylinder mould cover 10 (see Figure 10), the  
paper 16 incorporates a wide strip 13 of impermeable  
10 substrate, the edges of which are wholly embedded  
between the two surfaces of the paper 16 to hold the  
strip 13 securely in position. If the strip 13 is  
transparent, there will be one or more translucent or  
transparent windows 17 in the paper corresponding to  
15 the blinded areas 12.

A further example of paper which can be produced  
accordingly to the invention is shown in Figures 12 to  
16 in which a more complex design is used in the  
blinding of the cylinder mould cover 10. Here, the  
20 blinds used have variable height and/or width to  
produce various degrees of transparency in defined  
areas depending on whether the blinding material is  
covered by the strip 13 or not.

In a modification of the present invention as  
25 shown in Figures 17 to 21, the cylinder mould cover 10  
is produced in a known way, using dies to form the  
wire by embossing to form one or more raised areas 19.  
These raised areas 19 define the shape of the windows  
17 in the final paper 16. The top surfaces of the  
30 raised areas 19 are then blinded with blind material  
12. The width of the raised areas 19 is such that, as  
the impermeable strip 13 is brought into contact  
therewith below the level of the stock 11, its edges  
overhang the raised areas 19 on either side, as shown  
35 in Figure 20.

In either method, the impermeable strip 13 may  
have a uniform adhesive or other appropriate coating

- 11 -

on at least one side. Thus when the strip 13 is introduced into the vat of paper stock 11 (see Figure 1), the coated side of the strip 13 lies against the mould cover 10 (see Figure 22), to ensure that full bonding of the fibres and strip 13 takes place in the fibre bridges 18 and along the edges of the strip 13. Paper formation continues around the mould cover 10 forming over the edges of the strip 13. Few or no fibres are deposited over the non-adhesive coated areas mainly due to the width of the strip 13 as the substrate, from which it is preferably made, is preferably hydrophobic. However the adhesive coating is preferably hydrophilic and will tend to draw fibres away from the strip surface. The few fibres that are deposited on the non-adhesive coated areas will be subsequently removed by the press rolls and in the drying cylinders of the final stages of the typical paper-making process.

In an alternative embodiment of the present invention a hydrophobic coating may be used on the non-adhesive coated areas, to assist in preventing any fibre covering.

Where some fibres are deposited on the blinding material before the strip 13 is introduced, the paper fibre density thus formed is considerably reduced due to the lower percentage of fibres present than in the rest of the surrounding paper. This forms a clearly visible translucent or even transparent "stripe" 21 (see Figures 10 and 15) in both reflected and transmitted light on the first or "wire" side of the paper. Within this stripe 21, the strip 13 is partly exposed in the windows 17. On the second side of the paper, the "felt" side, the central section of the strip is wholly exposed. When larger blinds are used (Figures 2 to 6), less paper is formed before the strip 13 is introduced and the more transparent is the stripe 21. Where smaller blinds are used (Figures 7 to

- 12 -

11) more paper is formed so the stripe 21 is more translucent.

This process therefore enables a wide strip of an impermeable substrate, of a width in a range of say  
5 6mm to 25mm, to be included in a paper substrate. The width of the strip 13 could be very close to banknote width, so that in finished banknotes just a narrow margin of paper runs down each edge of the note. (NB: although the strip 13 in such a context may not be  
10 narrow and elongate and therefore appropriate to be described as a strip with respect to the finished banknote, it is a strip with respect to the full sheet of paper during manufacturing. Thus any reference in this specification to a "strip" should be interpreted  
15 accordingly). When viewed in reflection from the wire side, large transparent windows 17 can be made which are highly visible within the translucent stripe 21.

This wide strip 13 of impermeable substrate may be used as a display surface for indicia, for example,  
20 de-metallised images, holographic images, colour-shifting areas, print or combinations of any or all of these which are highly visible in the large windows 17. However, if a plain clear strip 13 is used, the windows 17 will be partially translucent or wholly  
25 transparent. When viewed in transmission, from the wire side the indicia, the metallisation or colouring on the fully embedded edges of the strip 13 also become visible. These edges may be provided with indicia which bleed from or complement any indicia  
30 contained on the exposed portion of the strip 13.

Depending on the width of the strip the windows 17 could be, for example, 20mm square or 5mm x 15mm rectangles.

When viewed from the felt side of the paper 16,  
35 the strip 13 itself can be seen in a continuous exposed area as a transparent, shiny, coloured or metallised area which may bear indicia, information or

- 13 -

imagery. The area may extend along the full length or width of the paper 16 or a substantial part thereof. Furthermore if the blinds with or without embossings form an image or geometric pattern other than straightforward rectangular or square windows 17, this pattern can be seen along the length of the strip 13, with the transparent strip 13 being wholly or partially visible with these windows.

One preferred material for the strip 13 is a PET strip of, say, 50 micrometers thickness as this would help to maintain the "bulk" of the paper 16 over the windowed region. However, other materials such as OPP, PE or PK with other thicknesses may be used. In one embodiment, de-metallised images are used which have large areas of transparent regions to provide a greater contrast within the windows between the metallised and non-metallised areas. When the paper 16 is viewed from the wire side of the paper 16, the visibility of the paper bridges 18 between the windows 17 is enhanced by its contrast to the metallisation.

In previous embodiments of the invention, it is described how an adhesive may be applied uniformly to one side of the strip 13, whilst the other side is coated with adhesive in bands and slit so that only the edges of the element 13 have the adhesive coating. Adhesive patterns could additionally be applied by a transfer or other type of printing process to provide additional paper patterns on the felt side of the paper 16.

However, in a further embodiment of the invention an adhesive or coating may be applied to the whole of both sides of the strip 13. This results in the deposition of a layer of paper on the felt side, such that the strip 13 is wholly covered on that side. In the region of the second part of the strip 13 the translucent stripe 20 is still clearly visible in comparison to the surrounding paper 16.

- 14 -

A standard adhesive or coating used in known processes for making embedded windowed security thread could be used, or any form of thermally activated adhesive or a water based adhesive which provides a hydrophilic surface to hold paper fibres during the initial stages of paper formation.

The combination of a wide strip 13 of impermeable substrate, preferably zero oscillation of the strip 13 during processing, and the blinding of the cover 10 enables the provision of other interesting features not currently available in the prior art. These include the modification of the paper bridges 18 to form designs and other indicia. Chevron, waves and other geometric patterns can be produced including more elaborate designs and alphanumeric patterns. Some examples are shown in Figures 23 and 24.

The use of electrotpe technology to create the blinds on the mould cover 10 allows regular transparent windows to be produced by using wide flat areas of plates in any shape. However, the use of narrow electrotpe does not produce transparent regions, but instead translucent regions which can be of fine detail. This provides a highly visible effect with the electrotpe image enhanced within the light band in the region of the strip 13.

The strip 13 can advantageously be used as an information carrier and/or can contain a wide variety of known security features. These may include the following;

- de-metallised designs, which may comprise areas of substantially removed metal to take advantage of the transparency of the base film and provide a large area of transparent window 17;
- holographic designs, which could comprise areas of full metal and half-tone screens to provide

- 15 -

partial transparency and/or no metal. Under certain viewing conditions, with no metal, a holographic image is still visible;

- 5 .. front to back print registration, in which features are printed which would clearly exhibit Moiré patterns from both front and back if a counterfeit were attempted. Alternatively, such patterns could be produced on a transparent film prior to insertion of the strip 13 into the paper as a security feature itself. The exact reproduction of such patterns are very difficult to mimic;
- 10
- 15 - different coloured print showing on the front to the back. The print may be on either side of the strip or both on the same side, with one colour hidden by the other on one side but showing through on the other side;
- 20
- 25 - liquid crystal films, such as those described in WO-A-94/02329, in which colour changes are visible when a molecular liquid crystal material is coated onto a watermark. Due to the scatter effect of the paper surface, a large percentage of the possible colour intensity is lost. By using a fully transparent window, a very vivid colour change is visible both in reflection and transmission;
- 30
- 35 - luminescent or magnetic materials;
- embedded de-metallised regions. As the areas of the strip 13 at each edge are completely embedded, these can contain a de-metallised type image which would only become visible when the document was viewed in transmission. This area



- 16 -

may also mimic a similar adjacent area which is visible in reflection and transmission or the metallisation could bleed out to the adjacent area;

5

- security embossing of transparent film with a security design (e.g. a treasury seal) created during the printing process. These may be blind embossed to produce a tactile/visible feature or could include printing inks to further enhance visibility;
- 10
- contact measurements in which at least one side of the strip is available for contact along its entire length. Measurements can include resistance measured on a current being passed through the strip; contact to microcircuitry embedded within the strip; contact to activate a material within the strip, e.g., PVDF
- 15
- 20 electrochromic; conductive polymers;
- the application of an adhesive or coating in a print process such as a transfer process to the continuously exposed side of the strip such that selective deposition of paper fibres also occurs
- 25 in those areas. These could form registered or non-registered designs, and would be difficult to reproduce by a counterfeiter. Figures 25 and 26 illustrate such a feature in which paper fibres
- 30 are selectively deposited to form images, patterns, alphanumeric numerals etc. e.g., 19a and 19b.

35 With such a large area available, it is possible to combine many features together on a strip 13.

In addition, the strip 13 could be perforated with holes of various shapes to provide novel features

- 17 -

or possibly machine readability, e.g. via airstreams,  
as shown in Figures 28, 29.

5 The paper 16 described above can be cut and  
printed to make all forms of documents, including  
security documents such as banknotes, cheques,  
travellers cheques, identity cards, passports, bonds  
etc.

10 A second ply of paper substrate could be  
laminated to paper as described above to completely  
obscure the visible effects of the strip 13 one side,  
if required.

15

20

25

30

35

- 18 -

CLAIMS:

1. A method of making single ply paper having an elongate impermeable strip at least partially embedded therein, comprising the steps of blinding one or more selected areas of a porous support surface, depositing a first layer of paper fibres onto the porous support surface around the blinded areas, bringing the strip to lie in contact with the blinded areas of the support surface such that at least edges of the strip over lie the deposited fibres, and depositing a further layer of paper fibres over the first layer and the impermeable strip to securely embed the edges of the strip within the paper, said blinded areas being impermeable to substantially prevent the deposition of fibres thereon before the security element is laid thereover and to thereby form a plurality of discrete translucent or transparent windows in a first surface of the paper in which regions of one side of the strip are exposed, wherein substantially no paper fibres are deposited along on an opposite side of the length of the strip in a region between the edges to thereby expose a continuous area of the strip at a second surface of the paper.
2. A method as claimed in claim 1 in which an adhesive or coating is applied to the one side of the strip before bringing that side into contact with the support surface.
3. A method as claimed in claim 2 in which an adhesive is applied to one or more portions of the other side of the strip.
4. A method as claimed in any one of the preceding claims in which the strip is not mechanically oscillated during manufacture of the paper.

- 19 -

5. Single ply paper made by the method of any one of the preceding claims having first and second surfaces and an elongate impermeable strip at least partially embedded therein, which edges of the strip are  
5 embedded fully between the first and second surfaces, and a continuous strip of a central section of one side of the strip is exposed at the first surface of the paper and another side of the strip is at least partially covered by a layer of paper of reduced  
10 opacity forming the second surface.

6. Single ply paper as claimed in claim 5 in which the second surface of the paper is provided with a plurality of discrete windows in which portions of the  
15 strip are exposed at intervals.

7. Single ply paper as claimed in claim 5 or claim 6 in which the width of the strip lies in the range of 6 to 25mm.  
20

8. Single ply paper as claimed in any one of claims 5 to 7 in which the strip bears indicia, images or information.

9. Single ply paper as claimed in any of the claims 5 to 8 in which the strip is wholly or partially metallised.  
25

10. Single ply paper as claimed in any one of claims 5 to 9 in which the strip bears one or more  
30 holographic images.

11. Single ply security paper as claimed in any one of claims 5 to 10 in which the strip has one or more  
35 colour shift areas.

12. Single ply paper as claimed in any one of claims

- 20 -

5 to 11 in which the strip has at least one security embossing.

13. Single ply paper as claimed in any one of claims  
5 5 to 12 in which the strip is printed on one or both sides.

14. Single ply paper as claimed in any one of claims  
10 5 to 13 in which the strip bears a liquid crystal material.

15. Single ply paper as claimed in any one of claims  
5 to 14 in which the strip has a thickness of 25 to 100 micrometers.

16. Single ply paper as claimed in claim 15 in which  
the strip has a thickness of 50 micrometers.







17. Single ply paper as claimed in any one of claims  
20 5 to 16 in which one side of the strip is coated with an adhesive.





18. Single ply paper as claimed in claim 17 in which  
the other side of the strip is partially coated with  
25 an adhesive in regions such that some paper is formed in the adhesive regions to provide paper patterns along the exposed central section of the strip.






19. A document produced from paper as claimed in any  
30 one of claims 5 to 18.

20. A security document produced from paper as  
claimed in any one of claims 5 to 18.

35














FIG. 22.




FIG. 23.





FIG. 24.








FIG. 28.





FIG. 29.



# INTERNATIONAL SEARCH REPORT

information on patent family members

Inter. natl Application No

PCT/GB 99/04257

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9401291 A	20-01-1994	SE 470400 B SE 9202110 A	14-02-1994 08-01-1994
EP 0625431 A	23-11-1994	DE 4314380 A AT 173201 T BR 9401667 A CA 2122528 A CN 1102865 A DE 59407255 D EP 0860298 A ES 2123072 T FI 942003 A NO 941538 A PL 173624 B SI 9400202 A US 5783275 A	03-11-1994 15-11-1998 06-12-1994 02-11-1994 24-05-1995 17-12-1998 26-08-1998 01-01-1999 02-11-1994 02-11-1994 30-04-1998 31-12-1994 21-07-1998

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**